

CellAdhere™ Tropoelastin, Human, Lyophilized

Purified tropoelastin, human, lyophilized, for tissue engineering research and cell culture

Catalog # 07003 1 mg



Scientists Helping Scientists™ | WWW.STEMCELL.COM

TOLL FREE PHONE 1 800 667 0322 • PHONE +1 604 877 0713

INFO@STEMCELL.COM • TECHSUPPORT@STEMCELL.COM

FOR GLOBAL CONTACT DETAILS VISIT OUR WEBSITE

Product Description

Tropoelastin is the water soluble precursor to the common structural protein elastin, formed by the crosslinking of tropoelastin monomers (Kozel et al.). Tropoelastin is a structural protein responsible for providing strength and elasticity to tissues in the body. Used as a cell culture surface coating, tropoelastin can promote cell attachment and spreading, while simultaneously allowing the modulation of surface elasticity (Holst et al.). Studies have shown that surface stiffness can have significant effects on cell growth and function.

CellAdhere™ Tropoelastin, Human, Lyophilized contains a single recombinant protein composed of entirely human sequences. This product is ideal for coating surfaces with a thin layer of protein to support cell attachment. The optimal protein concentration may vary depending on the cell type being used, and therefore must be titrated for best results.

Properties

Storage: Store at -20°C.

Shelf Life: Stable for 6 months from date of receipt.

Handling / Directions For Use

PREPARING TROPOELASTIN-COATED CULTUREWARE

1. Reconstitute CellAdhere™ Tropoelastin, Human, Lyophilized (1 mg) with 1 mL of sterile 0.25% acetic acid to obtain a 1 mg/mL solution.
2. Mix gently until solubilized.
NOTE: Reconstituted solution may be slightly opaque. If not used immediately, store at 2 - 8°C for up to 3 months.
3. Dilute reconstituted Tropoelastin solution with sterile 0.25% acetic acid to obtain desired concentration.
NOTE: Different dilutions will need to be tested to determine the optimal concentration required for each culture system. Typical coating concentrations range between 1 - 50 µg/mL.
4. Add desired amount of diluted Tropoelastin solution to the cultureware surface.
For example, use 1 mL to coat a 35 mm Culture Dish (Catalog #27100).
5. Cover coated cultureware to protect from contamination, and incubate at room temperature (15 - 25°C) for 1 - 2 hours.
6. Aspirate excess solution. Avoid scratching the coated surface.
7. Rinse coated cultureware with sterile distilled water.
8. Use coated cultureware immediately. Alternatively, keep sterile and store at 2 - 8°C damp or air dried.

References

Holst J et al. (2010) Substrate elasticity provides mechanical signals for the expansion of hemopoietic stem and progenitor cells. *Nat Biotechnol* 28(10): 1123–8.

Kozel BA et al. (2003) Domains in tropoelastin that mediate elastin deposition in vitro and in vivo. *J Biol Chem* 278(20): 18491–8.

STEMCELL TECHNOLOGIES INC.'S QUALITY MANAGEMENT SYSTEM IS CERTIFIED TO ISO 13485. PRODUCTS ARE FOR RESEARCH USE ONLY AND NOT INTENDED FOR HUMAN OR ANIMAL DIAGNOSTIC OR THERAPEUTIC USES UNLESS OTHERWISE STATED.

Copyright © 2018 by STEMCELL Technologies Inc. All rights reserved including graphics and images. STEMCELL Technologies & Design, STEMCELL Shield Design, Scientists Helping Scientists, and CellAdhere are trademarks of STEMCELL Technologies Canada Inc. All other trademarks are the property of their respective holders. While STEMCELL has made all reasonable efforts to ensure that the information provided by STEMCELL and its suppliers is correct, it makes no warranties or representations as to the accuracy or completeness of such information.